



Europäisches Patentamt  
European Patent Office  
Office européen des brevets

Publication number:

**0 367 504  
A2**



## EUROPEAN PATENT APPLICATION

Application number: 89311075.9

Int. Cl.<sup>5</sup> **C23C 22/68 , C23C 22/83 ,  
C09J 5/02**

Date of filing: 26.10.89

The application is published incomplete as filed (Article 93 (2) EPC). The point in the description (first line of original page 4) at which the omission obviously occurs has been left blank.

Priority: 01.11.88 GB 8825482

Date of publication of application:  
09.05.90 Bulletin 90/19

Designated Contracting States:  
**DE ES FR GB IT SE**

Applicant: The British Petroleum Company  
p.l.c.  
Britannic House Moor Lane  
London EC2Y 9BU(GB)

Inventor: Cayless, Richard Arthur  
The British Petroleum Co. p.l.c. Chertsey  
Road  
Sunbury-on-Thames Middlesex TW16  
7LN(GB)

Representative: Ryan, Edward Terrence et al  
**BP INTERNATIONAL LIMITED**, Patents  
Division Chertsey Road  
Sunbury-on-Thames Middlesex, TW16  
7LN(GB)

Surface treatment of metals.

Metal surfaces are heated with an aqueous treatment medium which is a solution of yttrium and metal of the lanthanum series or a suspension of particles of alumina with bound chromate followed by treatment with a solution of organosilane. Bonding of adhesives or surface coatings is improved.

EP 0 367 504 A2

## SURFACE TREATMENT OF METALS

This invention relates to a method of treating metal surfaces.

Organosilanes are known to be effective adhesion promoters for metal/polymer bonding. Such silanes are disclosed in "Silane Coupling Agents" by E.P. Plueddemann (Plenum Press, New York 1982).

Our copending application (Case 6688/6920) describes a method of treatment of a metal oxide layer, the metal oxide layer being in contact with metal in the bulk state and being formed by exposure to oxygen of the metal in the bulk state. The process is characterised in that the metal oxide layer is treated with an aqueous solution of a salt of a metal selected from a group consisting of yttrium and metals of the lanthanum series having atomic numbers from 57 to 71 inclusive for a continuous period of less than one day, the metal oxide being subsequently subjected to a drying process. The application also describes the application of an adhesive to the treated layer. However there is no suggestion that the performance of any such adhesive bond will be improved by further treatments.

Our copending patent application (Case 6689) describes a process for the treatment of a metal oxide layer, the metal oxide layer being in contact with a metal in the bulk state and being formed by exposure to oxygen in the bulk state. The process comprises treating the metal oxide layer with an aqueous medium containing a chromium compound and alumina in which any chromium present in solution in the aqueous medium is released from alumina particles which have been previously prepared so as to have chromate anions releasably bound to the alumina. Again there is no suggestion in this specification that the performance of adhesive bonds resulting from application of adhesive to the treated layer can be improved by a further treatment.

We have now found that improved bonding of organic materials such as adhesives to metal surfaces can be obtained by a two stage treatment.

According to the present invention there is provided a process for treating a metal surface characterised in that it comprises the steps of:

- (1) contacting the metal surface with an aqueous treatment medium which is:
  - a) a solution of a salt of a metal selected from the group consisting of yttrium and metals of the lanthanum series having atomic numbers from 57 to 71 inclusive, or
  - b) an aqueous suspension of alumina particles to the surface of which particles chromate anions are chemically bound, and

- (2) subsequently contacting the metal surface with a solution of an organosilane.

It has been found that the use of organosilanes in conjunction with certain inorganic metal surface treatments gives surprising results in adhesion promotion. The organosilane can be chosen from a wide variety of such reagents. The organosilane will preferably contain an alkoxy group preferably ethoxy or methoxy. In particular it is preferred that the organosilane is an aminosilane or an epoxy silane. The amino silane is preferably 3-(2-amino ethyl amino) propyl trimethoxy silane. The epoxy silane is preferably 2-(3-glycidyloxy) propyl trimethoxy silane.

Where the metal surface is contacted with aqueous solutions of a salt of yttrium or of a lanthanide metal, the salt is preferably a salt of yttrium, samarium or cerium. The solutions referred to can either be solutions of salts of individual metals or they can be solutions of mixed metal salts. Mixed metal salts may be derived from natural ores where the occurrence of several metals is known. The counter anion is preferably the nitrate anion because of its relatively high solubility in water. The concentration of the applied metal salt solutions can be in the range  $10^{-1}$  -  $10^{-6}$  M, preferably  $10^{-2}$  -  $10^{-6}$  M, more preferably in the range  $10^{-3}$  -  $10^{-5}$  M, for example in the range  $5.0 \times 10^{-3}$  -  $5.0 \times 10^{-4}$  M.

The aqueous suspension of alumina to the surface of which chromate anions are chemically bound is preferably an aqueous suspension such as is disclosed in our copending application (Case 6689) in which any chromium present in the aqueous medium originates from alumina particles which have been previously prepared so as to have chromate anions releasably bound to the alumina. The aqueous medium preferably contains as an active ingredient substantially only alumina particles having chromate releasably bound to alumina. The alumina having chromate anions chemically bound to its surface is referred to in the specification as "chromate alumina". "Chromate alumina" may be prepared by the method described in GB 2 071 070B. The alumina will have a chromium content (as determined by XRF) which can be in the range 0.1 - 6% w/w, preferably in the range 1 - 5% w/w, more preferably in the range 2 - 3% w/w. In general the alumina will preferably have a high level of surface hydroxyl groups. Examples of suitable aluminas are the commercially available activated aluminas sold under the name "Camag" and defined as having a Brockman Activity 1 for chromatography and F1 aluminas sold by the Aluminium Company of America.

Suitable particle sizes may be up to 100 micrometres diameter. The preferred particle size range is 2 -

10 micrometres. The chromate anion is releasably bound to the alumina. When the alumina is suspended in water, the chromate anion is released and has a finite concentration in solution.

Aqueous solutions of a salt of yttrium or of a lanthanide metal or aqueous suspensions of alumina to the surface of which chromate anions are chemically bound can be applied by any of the usual techniques used for applying reagent solutions to metal surfaces e.g. dipping, spraying, flooding etc.

10

organic solvent, although water can be used. An example of an organic solvent is toluene. Concentration of the organosilane is preferably in the range 0.5 - 2% w.w.

15 The present invention is applicable to most metals, in particular steel, aluminium and zinc, preferably steel, more preferably cold rolled mild steel. The metal surface in the present invention may have undergone an initial cleaning step, for the purposes, for example, of removing temporary protective materials such as oil. This cleaning may be by chemical means (alkaline wash) by mechanical means (abrading) or a solvent wash may be used; such methods are well known in the art. Furthermore, the metal  
 20 may be subsequently stored after treatment so that it may be used at a later date. For example, steel may be covered in a protective oil to prevent corrosion. The treatment of the present invention is storage resistant and the adhesion promotion effect is not adversely affected by such storage methods.

The treatment of metal surfaces in consecutive steps comprising treatment with an inorganic metal surface reagent followed by treatment with a solution of an organosilane is suitably used in conjunction with  
 25 polymeric organic adhesives. Examples of such adhesives are epoxy resins, acrylic resins, polyurethane resins, vinyl resins, and phenolic resins, preferably epoxy resins. The organosilane can be applied prior to application of the adhesive, or alternatively it can be added to the adhesive formulation itself which can be then applied as a solution in the adhesive after the metal surface has been contacted with a) an aqueous solution of yttrium or of a lanthanide metal or b) an aqueous suspension of alumina to the surface of which  
 30 chromate anions are chemically bound.

The invention may be used to increase adhesive bond strengths and to enhance the durability of adhesive bonds, particularly in aqueous environments. A typical structure using the present invention would comprise two metal objects treated according to the invention and bonded together using an adhesive. The metal objects may be different parts of the same structure. Thus the two ends of a metal sheet may be  
 35 bonded together to form a tube.

The adhesion of an organic polymer surface coating to a metal surface can also be enhanced by treatment of the metal surface according to the present invention. The invention is now illustrated with reference to the following examples.

40

#### Adhesion Test Method

Mild steel test pieces (pretreated as described below) were bonded with epoxy adhesive to determine the adhesive properties of treated and untreated steel. The test pieces measured 2.54 cm by 6.35 cm and  
 45 were cut from 0.75 mm steel paint test panels supplied by the Pyrene Chemical Services Ltd. This is grade CR1 cold rolled steel polished on one side only and supplied coated with a protective oil to prevent rusting. The adhesive was a simple commercially available epoxy resin; Shell Epikote 828 cured with DMP30 hardener (Anchor Chemical Company). 10 parts adhesive were mixed with one part of hardener (by weight) immediately prior to use. The steel was cleaned in an ultrasonic solvent degreasing bath (1,1,1-trichloroethylene) to remove the protective oil prior to any treatment. 2.54 cm square lap bonds were prepared  
 50 by bonding the ends of the polished sides of two test pieces together with a 2.54 cm overlap. Bond line thickness was approximately 1 mm. The adhesive was then cured at 80 °C for 1 hour.

A total of 8 such samples were prepared for each treatment. Of these, four were subjected to a durability test (400 hours immersion in distilled water at 50 °C) to determine the effect of hot wet  
 55 environments on joint strength. The bond strength of the joints was determined using an Instron materials testing machine in which samples are pulled apart at constant speed and the load required to cause failure is recorded. The bonded samples are 10.16 cm long (2x6.35 cm - 2.54 cm overlap), of this 1.27 cm at each end is used by the test machine grips to hold the sample. The samples were pulled apart at 0.5mm/minute

under ambient conditions. The durability (water immersion) samples were tested immediately after removal from the water.

The results of the adhesion test are recorded as average failure strengths in Table I. The percentage loss of adhesion on water immersion is also given.

- 5 Test pieces were treated according to the invention as indicated below; these pieces were then tested according to the above method. Comparative tests were carried out as described. Results are given in Table I.

#### 10 Preparation of Chromate Alumina

- 500 litres of water are charged to a reaction vessel at ambient temperature and the agitator started. 500Kg of  $\text{Al}_2\text{O}_3$  are then added together with a sufficient amount of additional water to maintain effective agitation. The pH is monitored and  $\text{CrO}_3$  added steadily such that the pH does not fall below 1. Agitation is maintained until the pH effectively stops rising. The mixture is left standing for 30 minutes. The product is then washed with deionised water to a wash water conductivity of 1.000 micro ohms per cm. The washing process involves slurrying with fresh water allowing the product to settle, decantation of the mother liquor then repeating the process. The product is finally reslurried to a solids content suitable for spray-drying. The slurry is wet ground to the desired particle size, then spray-dried. The product is micronised (finely ground) in a large ball mill to a particle size of less than 10 microns and then stored in air-tight containers.

The alumina used was Alcoa F1 (granular) supplied by Alcoa and the chromium content (%w:w) of the final dried product was 2.7% as determined by XRF.

#### 25 Comparative Test A (not according to the invention)

Test pieces were tested according to the method described above, the test pieces receiving no pretreatment other than described in the method.

#### 30 Comparative Test B (not according to the invention)

- Steel test pieces as described above were treated by immersion in a 5% wt suspension of chromate alumina in water (100 ml per plate) for 3 minutes followed by three 1 minute washes in distilled water to remove excess material, then dried by dabbing on a tissue. Adhesive bonds were prepared and tested as described above. The results of initial strength and durability testing are given in Table I.

#### 40 Comparative Test C (not according to the invention)

Test pieces were immersed in a  $10^{-4}$  molar solution of yttrium nitrate in distilled water for 5 minutes, they were then rinsed twice using distilled water and dried on a tissue. The test pieces were then tested according to the method described above.

- Pure compounds such as yttrium nitrate are relatively costly. Commercially available mixtures of rare earth nitrates which are much cheaper can also be used in treating test pieces (see Comparative Test D).

#### Comparative Test D (not according to the invention)

- 50 Treatment of test pieces was carried out according to the method described in Comparative Test C but using commercially available mixed rare earth metal nitrates. The test pieces were then tested according to the test described above.

#### 55 Comparative Test E (not according to the invention)

Test pieces were immersed in a 1% w/w solution of the aminosilane  $(\text{CH}_3\text{O})_3\text{Si}(\text{CH}_2)_3\text{NH}(\text{CH}_2)_2\text{NH}_2$  then washed 3 times for 1 minute in toluene. The plates were allowed to dry, excess toluene being removed

with a tissue, bonded and tested as described above.

**BEST AVAILABLE COPY**

Example 1 (according to the invention)

Test pieces were treated as described in Comparative Test B, then treated with aminosilane as described in Comparative Test E. The test pieces were bonded and tested as described above.

Example 2 (according to the invention)

Test pieces were treated as described in Comparative Test C, then treated with aminosilane as described in Comparative Test E. The test pieces were bonded and tested as described above.

Example 3 (according to the invention)

Test pieces were treated as described in Comparative Test D, then treated with aminosilane as described in comparative Test E. The test pieces were bonded and tested as described above.

Example 4 (according to the invention)

Test pieces were treated as described in Comparative Test B. The test pieces were bonded and tested as described above except that 1% by weight of the aminosilane  $(\text{CH}_3\text{O})_3\text{Si}(\text{CH}_2)_3\text{NH}(\text{CH}_2)_2\text{NH}_2$  was added to the epoxy adhesive prior to bonding.

Comparative Test F (not according to the invention)

Test pieces were treated as described in Comparative Test A. The test pieces were bonded and tested as discussed above except that 1% by weight of the aminosilane  $(\text{CH}_3\text{O})\text{Si}(\text{CH}_2)_3\text{NH}(\text{CH}_2)_2\text{NH}_2$  was added to the epoxy adhesive prior to bonding.

Results of all the testing according to the method described above for Comparative Tests A-F and Examples 1-5 are given in Table I.

The yttrium nitrate was supplied by BDH. The rare earth metal nitrate was supplied by Rare Earth Products (Widnes, Cheshire) as a solution of the metal oxides neutralised with nitric acid and subsequently diluted as needed.

The aminosilane was supplied by Fluka.

Alcoa, Epikote and Instron are all Trade Marks.

TABLE I

TEST EXAMPLE	TREATMENT	INITIAL STRENGTH	400HR STRENGTH	% LOSS
A	Untreated	3.33	2.45	26
B	Chromate Alumina No aminosilane	3.67	3.20	13
C	$\text{Y}(\text{NO}_3)_3$ No aminosilane	3.39	2.86	16
D	Mixed rare earth metal nitrates. No aminosilane	3.53	3.04	14
E	Aminosilane	4.01	3.01	25
1	Chromate Alumina/aminosilane	4.01	3.71	7.5
2	$\text{Y}(\text{NO}_3)_3$ /aminosilane	4.33	3.78	12.7
3	Mixed rare earths/aminosilane	4.42	4.05	8.4
4	Chromate alumina/aminosilane in adhesive	3.87	3.82	1.5
F	Aminosilane in adhesive	3.79	3.01	21

## Claims

1. A process for treating a metal surface characterised in that it comprises the steps of:
  - (1) contacting the metal surface with an aqueous treatment medium which is:
    - 5 a) a solution of a salt of a metal selected from the group consisting of yttrium and metals of the lanthanum series having atomic numbers from 57 to 71 inclusive, or
    - b) an aqueous suspension of alumina particles to the surface of which particles chromate anions are chemically bound, and
  - (2) subsequently contacting the metal surface with a solution of organosilane.
- 10 2. A process according to claim 1 wherein the metal surface is treated with an aqueous solution of yttrium, samarium or cerium.
3. A process according to either of claims 1 or 2 wherein the metal surface is treated with an aqueous solution of a nitrate salt of a metal selected from the group consisting of yttrium and metals of the lanthanum series having atomic numbers from 57 to 71 inclusive.
- 15 4. A process according to any one of the preceding claims wherein the concentration of the salt of the metal selected from the group consisting of yttrium and metals of the lanthanum series is in the range  $10^{-3}$  -  $10^{-5}$  M.
5. A process according to claim 1 wherein the metal is treated with an aqueous suspension of alumina with a chromium content in the range 0.1 to 6% weight.
- 20 6. A process according to claim 5 wherein the chromium content is the range 1-5% weight.
7. A process according to claim 6 wherein the chromium content is in the range 2-3% weight.
8. A process according to any one of claims 1, 4, 5 or 6 wherein the alumina particles have a diameter up to 100 micrometres.
9. A process according to claim 8 wherein the particle sizes are in the range 2-10 micrometres.
- 25 10. A process according to any one of the preceding claims wherein the organosilane contains an alkoxy group.
11. A process according to claim 10 wherein the alkoxy group is ethoxy or methoxy.
12. A process according to any one of the preceding claims wherein the organosilane is an aminosilane or an epoxy silane.
- 30 13. A process according to any one of the preceding claims which comprises applying a layer of an organic polymer surface coating subsequently to or simultaneous with the step of contacting the metal surface with an organo-silane.
14. A structure comprising two metal objects having treated surfaces which have
  - (1) been treated by being contacted with an aqueous treatment medium which is:
    - 35 a) a solution of a salt of a metal selected from the group consisting of yttrium and metals of the lanthanum series having atomic numbers from 57 to 71 inclusive, or
    - b) an aqueous suspension of alumina particles to the surface of which particles chromate anions are chemically bound, and
  - (2) subsequently been contacted with a solution of an organo silane, and
  - 40 (3) bonded together by a layer of a polymeric organic adhesive.

(19)



Eur päisches Patentamt  
European Patent Office  
Office européen des brevets

**BEST AVAILABLE COPY**

(11) Publication number:

**0 367 504  
A3**

(12)

**EUROPEAN PATENT APPLICATION**

(21) Application number: 89311075.9

(51) Int. Cl.<sup>5</sup>: **C23C 22/68, C23C 22/83,  
C09J 5/02**

(22) Date of filing: 26.10.89

(30) Priority: 01.11.88 GB 8825482

(43) Date of publication of application:  
09.05.90-Bulletin 90/19

(64) Designated Contracting States:  
**DE ES FR GB IT SE**

(69) Date of deferred publication of the search report:  
29.08.90 Bulletin 90/35

(71) Applicant: The British Petroleum Company  
p.l.c.  
Britannic House Moor Lane  
London EC2Y 9BU(GB)

(72) Inventor: Cayless, Richard Arthur  
The British Petroleum Co. p.l.c. Chertsey  
Road  
Sunbury-on-Thames Middlesex TW16  
7LN(GB)

(74) Representative: Ryan, Edward Terrence et al  
BP INTERNATIONAL LIMITED, Patents  
Division Chertsey Road  
Sunbury-on-Thames Middlesex, TW16  
7LN(GB)

(54) Surface treatment of metals.

(57) Metal surfaces are heated with an aqueous treatment medium which is a solution of yttrium and metal of the lanthanum series or a suspension of particles of alumina with bound chromate followed by treatment with a solution of organosilane. Bonding of adhesives or surface coatings is improved.

**EP 0 367 504 A3**



European Patent  
Office

# EUROPEAN SEARCH REPORT

Application number

EP 89 31 1075

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
P,X	EP-A-0 331 284 (THE BRITISH PETROLEUM CO.)		C 23 C 22/68 C 23 C 22/83 C 09 J 5/02
	* Claims 1-11 *	1-4, 10-14	
Y	PATENT ABSTRACTS OF JAPAN, vol.10, no. 172 (C-354)(2228), June 18, 1986 & JP-A-61 23 766 (SUMITOMO KINZOKU KOGYO K.K.) 01-02-1986		
	* Abstract *	1,5-7, 14	
Y	FR-A-2 227 350 (PENNWALT CORP.) * Claims 1-9 *	1,5-7, 14	
A	PATENT ABSTRACTS OF JAPAN, vol. 9, no. 52 (C-269)(1775) March 6, 1985 & JP-A-59 193 280 (NITSUSHIN SEIKOU K.K.) 01-11-1984 * Abstract *	1,5-7, 14	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
A	US-A-3 592 681 (H.HATWELL et al.) * Claims 1-13 *	1,5-7, 14	C 23 C C 09 J C 23 F
A	US-A-3 969 152 (D.J. MELOTIK) * Claims 1-5; column 4, lines 49-51	1	
A	DE-A-2 334 342 (STAUFFER CHEM. CO.)	1	
A	FR-A-2 183 582 (J.A. TAVIERE)	1	
The present search report has been drawn up for all claims			
Place of search The Hague		Date of completion of the search 16-05-1990	Examiner DE ANNA

## CATEGORY OF CITED DOCUMENTS

X : particularly relevant if taken alone  
Y : particularly relevant if combined with another document of the same category  
A : technological background  
O : non-written disclosure  
P : intermediate document

T : theory or principle underlying the invention  
E : earlier patent document, but published on, or after the filing date  
D : document cited in the application  
L : document cited for other reasons  
& : member of the same patent family, corresponding document